

Sylvin 5175-92 Brown 7314

Polyvinyl Chloride
Sylvin Technologies Incorporated

Message:

Sylvin 5175-92 Brown 7314 Is A RoHS Compliant, Vinyl Compound Formulated For Wire And Cable Applications. This Compound Has A UL Approval For TW, THW, THHW And 720 Hour Sunlight Resistance And CSA Approval For Flexible Cord Insulation.

General Information			
Uses	Wire and cable applications		
Wire Types	THHW		
	THW		
	TW		
Agency Ratings	CSA not rated		
RoHS Compliance	RoHS compliance		
Appearance	Brown		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	92		ASTM D2240
Shaw A, 10 seconds	92		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	18.6	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	105	°C	ASTM D794
Brittleness Temperature	-16.0	°C	ASTM D746
Melting Temperature	171 - 182	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ASTM D2863
Flammability	VW-1		UL 1581

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

