

KANEKA H727

Chlorinated Polyvinyl Chloride

Kaneka North America LLC

Message:

KANEKA H727 is a Chlorinated Polyvinyl Chloride material. It is available in Latin America or North America.

General Information			
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ASTM D638
Tensile Strength (Yield)	55.0	MPa	ASTM D638
Tensile Elongation (Break)	85	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	177	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	107	°C	ASTM D648
Vicat Softening Temperature	122	°C	ASTM D1525 ¹
NOTE			

1. Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

