

# YUPLENE® BH3530

Polypropylene  
SK Global Chemical

Message:

YUPLENE® BH3530 is a Polypropylene product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of YUPLENE® BH3530 include appliances, automotive, electrical/electronic applications and industrial applications. Primary characteristic: impact resistant.

General Information			
Features	Ultra High Impact Resistance		
Uses	Appliances		
	Automotive Applications		
	Electrical/Electronic Applications		
	Industrial Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	22.6	MPa	ASTM D638
Tensile Elongation (Break)	< 500	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	98	J/m	
23°C	> 490	J/m	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	150	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT