RTP 1200 S-40D

Thermoplastic Polyurethane Elastomer (Polyester)

RTP Company

Message:

RTP 1200 S-40D is a thermoplastic polyurethane elastomer (polyester)(TPU-polyester) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

| General Information | | | |
|------------------------------------|----------------------|-------|-------------|
| RoHS Compliance | Contact manufacturer | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.20 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow (3.20 mm) | 1.0 | % | ASTM D955 |
| Moisture Content | 0.020 | % | |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 40 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Modulus | 68.9 | MPa | ASTM D790 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 34.5 | MPa | ASTM D412 |
| Tensile Elongation (Yield) | 800 | % | ASTM D412 |
| Tear Strength ¹ | 123 | kN/m | ASTM D624 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 87.8 | °C | |
| Drying Time | 6.0 | hr | |
| Dew Point | -34.4 | °C | |
| Processing (Melt) Temp | 193 - 218 | °C | |
| Mold Temperature | 15.6 - 32.2 | °C | |
| Injection Pressure | 34.5 - 68.9 | MPa | |
| Injection instructions | | | |
| Desiccant Type Dryer Required. | | | |
| NOTE | | | |
| 1. | C mould | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

