

KOCETAL® CF302BK

Acetal (POM) Copolymer

Kolon Plastics, Inc.

Message:

KOCETAL® CF302BK is an Acetal (POM) Copolymer product filled with carbon fiber. It is available in Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

Conductive

High Stiffness

General Information			
Filler / Reinforcement	Carbon Fiber		
Features	Electrically Conductive		
	High Stiffness		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.90	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.22	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	87		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	105	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	2.5	%	ASTM D638
Flexural Modulus (23°C)	9780	MPa	ASTM D790
Flexural Strength (23°C)	156	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	3.0	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	164	°C	
1.8 MPa, Unannealed	160	°C	
Melting Temperature	166	°C	ASTM D1525
CLTE - Flow	6.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3	ohms	ASTM D257
Volume Resistivity	1.0E+2	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

