

Badamid® PA612 GF30

Polyamide 612

Bada AG

Message:

Badamid® PA612 GF30 is a Polyamide 612 (Nylon 612) material filled with 30% glass fiber. It is available in Europe for injection molding. Primary attribute of Badamid® PA612 GF30: Flame Rated.

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Processing Method		Injection Molding		
Resin ID (ISO 1043)		>PA612-GF30<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.30	--	g/cm ³	ISO 1183
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	8300	7800	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	142	128	MPa	ISO 527-2/1A/5
Tensile Strain (Break, 23°C)	3.0	3.3	%	ISO 527-2/1A/5
Flexural Stress (23°C, 4.00 mm)	195	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	80	--	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	212	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	196	--	°C	ISO 75-2/A
Melting Temperature (DSC) 1	218	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (1.00 mm)	1.0E+12	--	ohms·cm	IEC 60093
Electric Strength (1.00 mm)	35	--	kV/mm	IEC 60243-1
Comparative Tracking Index	550	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm	HB	--		
1.60 mm	HB	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	

Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	240 to 280	°C
Mold Temperature	60.0 to 90.0	°C

NOTE

1.	10 K/Min
----	----------

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

