

PREPERM® L900HF

Polyphenylene Ether

Premix Oy

Message:

PREPERM® L900HF is a special compound with elevated dielectric constants of 9.0.

PREPERM® L900HF is a special compound based on Premix proprietary PPE technology. Extremely low dissipation factor (< 0.001) makes PREPERM® L900HF an excellent material for high frequency applications. PREPERM® L900HF offers stable dielectric constant over wide frequency and wide temperature range. PREPERM® L900HF is modified for injection moulding.

Applications include structural parts for antennas in base stations, point to point, wlan, mobile phones etc. Devices made out of PREPERM® can operate at very high frequencies as PREPERM® offers stable performance even at 120 GHz.

General Information			
Uses	Electrical/Electronic Applications Electrical components		
RoHS Compliance	RoHS compliance		
Forms	Particles		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	2.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	12	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.40	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (4.00 mm)	50.0	MPa	ISO 527-2
Tensile Strain (Break, 4.00 mm, Injection Molded)	4.0	%	ISO 527-2
Flexural Modulus (4.00 mm)	4500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ¹ (23°C)	4.0	kJ/m ²	ISO 180
Unnotched Izod Impact Strength ² (23°C)	30	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	130	°C	ISO 75-2/Bf
1.8 MPa, not annealed	105	°C	ISO 75-2/Af
Electrical	Nominal Value	Test Method	
Dielectric Constant (1.00 GHz)	9.00	Internal method	
Dissipation Factor (1.00 GHz)	4.0E-4	Internal method	
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 100	°C	
Drying Time	2.0 - 4.0	hr	
Processing (Melt) Temp	280 - 310	°C	
Mold Temperature	80.0 - 110	°C	

Injection Rate	Moderate-Fast
Injection instructions	
Injection Pressure: High	
NOTE	
1.	4 mm thickness
2.	4 mm thickness

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

