

Franprene TGA 3350

Styrene Butadiene Styrene Block Copolymer

Franplast S.r.l.

Message:

SBS based compound with good over-moulding on PS. Eligible to provide large-scale retail items with grip and soft touch.

Application:

Hanger Clips (Clothing)

General Information			
Features	Soft		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	40	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	50		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	4.50	MPa	ISO 527-2
Nominal Tensile Strain at Break	700	%	ISO 527-2
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	20	kN/m	ISO 34-1
Thermal	Nominal Value	Unit	
Service Temperature	-30 to 60	°C	
Injection	Nominal Value	Unit	
Drying Time	0.0	hr	
Rear Temperature	145 to 165	°C	
Middle Temperature	150 to 170	°C	
Front Temperature	150 to 170	°C	
Nozzle Temperature	155 to 175	°C	
Mold Temperature	30.0 to 40.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT