

Lotryl® 35BA320

Ethylene Butyl Acrylate Copolymer

Arkema

Message:

LOTRYL® 35BA320 is a random copolymer of Ethylene and Butyl Acrylate produced by high-pressure radicalar polymerization process.

Applications

Due to the high butyl acrylate content, LOTRYL® 35BA320 can be used for applications where flexibility and polarity are required. Combined with a high fluidity, LOTRYL® 35BA320 is particularly recommended for the formulation of hot melt adhesives. It can also be used as processing-aid in highly filled compounds.

General Information			
Features	Good Flexibility		
	Random Copolymer		
Uses	Adhesives		
	Plastics Modification		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	260 to 350	g/10 min	ASTM D1238, ISO 1133
n-Butyl Acrylate Content	33.0 to 37.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, Compression Molded)	52		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, Compression Molded)	2.00	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break, Compression Molded)	200	%	ASTM D638, ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	< 40.0	°C	ISO 306/A, ASTM D1525 ¹
Melting Temperature	65.0	°C	ISO 11357-3
Ring and Ball Softening Point	85	°C	ASTM E28
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	150 to 170	°C	
Cylinder Zone 2 Temp.	170	°C	
Cylinder Zone 3 Temp.	170	°C	
Cylinder Zone 4 Temp.	170	°C	
Die Temperature	170	°C	
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

