

LNP™ THERMOCOMP™ AF002XXC compound

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

LNP THERMOCOMP* AF002XXC is a compound based on ABS resin containing 10% Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound AF-1002 HP

Product reorder name: AF002XXC

General Information			
UL YellowCard	E121562-101344528		
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.40	%	ASTM D955
Across Flow : 24 hr	0.40	%	ASTM D955
Across Flow : 24 hr	0.38	%	ISO 294-4
Flow : 24 hr	0.41	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.38	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4140	MPa	ASTM D638
--	4200	MPa	ISO 527-2/1
Tensile Strength			
Break	66.9	MPa	ASTM D638
Break	64.9	MPa	ISO 527-2
Tensile Elongation			
Break	2.5	%	ASTM D638
Break	2.7	%	ISO 527-2
Flexural Modulus			
--	4210	MPa	ASTM D790
--	4500	MPa	ISO 178
Flexural Strength			
--	106	MPa	ASTM D790
--	108	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	80	J/m	ASTM D256
23°C ²	9.0	kJ/m ²	ISO 180/1A

Unnotched Izod Impact			
23°C	320	J/m	ASTM D4812
23°C ³	24	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	15.3	J	ASTM D3763
--	3.30	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	102	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	92.8	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	95.0	°C	ISO 75-2/Af
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, Testing by SABIC)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050 to 0.10	%	
Rear Temperature	204 to 216	°C	
Middle Temperature	232 to 243	°C	
Front Temperature	266 to 277	°C	
Processing (Melt) Temp	260	°C	
Mold Temperature	71.1 to 82.2	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT