

Rilsan® CLEAR G 850 Rnew L

Polyamide 11

Arkema

Message:

Rilsan ® Clear G850 Rnew L is a high performance transparent polyamide having outstanding purity level and partially based on renewable resources. This grade has been specially designed for high quality optical lens applications, such as non corrective sun lenses or reading glasses.

MAIN APPLICATIONS

Non corrective sun lenses.

Polarized sun glass lenses.

General Information			
Features	Renewable Resource Content		
Uses	Optical Applications		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 40°C, 24 hr, 2.00 mm	0.75	%	
Flow : 40°C, 24 hr, 2.00 mm	0.60	%	
Water Absorption			ISO 62
23°C, 24 hr	4.0	%	
Equilibrium, 23°C, 50% RH	1.7	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	80		
Shore D, 15 sec	78		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1670	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	61.0	MPa	
Break	55.0	MPa	
Tensile Strain			ISO 527-2
Yield	8.0	%	
Break	> 100	%	
Flexural Modulus	1630	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	7.0	kJ/m ²	
23°C	7.5	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179

-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	135	°C	ISO 75-2/B
1.8 MPa, Unannealed	120	°C	ISO 75-2/A
Glass Transition Temperature	150	°C	ISO 11357-2
Optical	Nominal Value	Unit	Test Method
Transmittance (2000 μm, 560 nm)	91.7	%	ASTM D1003
Refractive Index	1.5030		ISO 489
Renewable Carbon Content	45	%	ASTM D6866
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	4.0 to 6.0	hr	
Processing (Melt) Temp	250 to 300	°C	
Mold Temperature	20.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

