

RTP 400 UV

Polystyrene Alloy

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Additive	UV stabilizer		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Molding Shrinkage - Flow			ASTM D955
3.18mm, injection molding	0.40	%	ASTM D955
6.35mm, injection molding	0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.040	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	3100	MPa	ASTM D638
Tensile Strength	52.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	2.4	%	ASTM D638
Flexural Modulus (Injection Molded)	3450	MPa	ASTM D790
Flexural Strength (Injection Molded)	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm, Injection Molded)	27	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	160	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, injection molded	96.0	°C	ASTM D648
1.8 MPa, unannealed, injection molded	79.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94

Additional Information

The value listed as Flammability, UL 94, was tested in accordance with RTP Company methods.

Injection	Nominal Value	Unit
Rear Temperature	204 - 238	°C
Middle Temperature	204 - 238	°C
Front Temperature	204 - 238	°C
Mold Temperature	38.0 - 66.0	°C
Injection Pressure	69.0 - 103	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

