

Braskem PE GP5550BX

High Density Polyethylene

Braskem

Message:

GP5550 is a High Density Polyethylene with high molar mass. It is produced with bimodal technology and shows excellent mechanical properties and high resistance to stress cracking. GP5550BK contains carbon black pigment that protects it against the ultraviolet radiation action and photodegradation.

General Information			
Features	Bimodal Molecular Weight Distribution		
	High ESCR (Stress Crack Resist.)		
	High Molecular Weight		
Uses	Cable Jacketing		
	Geo Membranes		
	Piping		
	Wire & Cable Applications		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Extrusion		
	Pipe Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.960	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	0.30	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 2.00 mm, 100% Igepal, Compression Molded, F50)	> 1000	hr	ASTM D1693
Carbon Black Content	2.0 to 2.5	%	ASTM D1603
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	64		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, Compression Molded	23.0	MPa	
Break, Compression Molded	38.0	MPa	
Tensile Elongation			ASTM D638
Yield, Compression Molded	8.4	%	
Break, Compression Molded	780	%	
Flexural Modulus - 1% Secant (Compression Molded)	1200	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (Compression Molded)	300	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, Compression Molded)	71.0	°C	ASTM D648
Vicat Softening Temperature	125	°C	ASTM D1525 ¹
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

