

WONDERLOY® PC-365

Polycarbonate + ABS
CHI MEI CORPORATION

Message:

WONDERLOY® PC-365 is a Polycarbonate + ABS (PC+ABS) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

- Flame Rated
- RoHS Compliant
- Heat Resistant
- Impact Resistant

General Information			
UL YellowCard	E56070-100239177		
Features	High Impact Resistance		
	Medium Heat Resistance		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm³	ASTM D792, ISO 1183
Spiral Flow	9.80	cm	Internal Method
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.40	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield, 23°C	53.0	MPa	ASTM D638
Yield	50.0	MPa	ISO 527-2/50
Break	46.0	MPa	ISO 527-2/50
Tensile Elongation			
Break, 23°C	85	%	ASTM D638
Break	80	%	ISO 527-2/50
Flexural Modulus			
23°C	2260	MPa	ASTM D790
-- ¹	2300	MPa	ISO 178
Flexural Strength			
23°C	78.5	MPa	ASTM D790
-- ²	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			

3.18 mm	540	J/m	ASTM D256
--	45	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed ³	106	°C	ASTM D648, ISO 75-2/A
1.8 MPa, Annealed	117	°C	ISO 75-2/A
Vicat Softening Temperature			
--	136	°C	ASTM D1525, ISO 306/A50 7 ⁴
--	123	°C	ISO 306/B50
CLTE - Flow (40 to 100°C)	6.0E-5 to 8.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	HB		
3.00 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	4.0	hr	
Rear Temperature	200 to 230	°C	
Middle Temperature	230 to 270	°C	
Front Temperature	220 to 260	°C	
Mold Temperature	50.0 to 100	°C	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	120°C/hr		
4.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

