

KW Plastics KW 621-T30

Polypropylene Impact Copolymer

KW Plastics

Message:

Copolymer Impact Polypropylene with 30% Talc Post-Consumer Resin

Injection Molding

CHARACTERISTICS

30% talc reinforced for improved stiffness, heat distortion, shrink rate and cycle time.

General Information			
Filler / Reinforcement	Talc,30% Filler by Weight		
Recycled Content	Yes		
Features	Impact Copolymer		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	23.4	MPa	ASTM D638
Tensile Elongation (Yield)	3.0	%	ASTM D638
Flexural Modulus	2280	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648B
0.45 MPa, Unannealed	116	°C	
1.8 MPa, Unannealed	60.8	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT