# TROGAMID® TCR Film 250 µm

### Polyamide

**Evonik Industries AG** 

#### Message:

Decorative effects by insert molding Resistant to chemicals High heat deflection temperature Clear and transparent

General Information

TROGAMID® TCR films are tough and stand up to sunlight, heat, shock, cosmetics, and chemicals.

Features	Durable				
	Good Abrasion Resistance				
	Good Chemical Resistance				
	Good Processability				
	Good Toughness				
	Good UV Resistance				
	Good Weather Resistance				
	Shock Resistant				
	Sunlight Resistant				
Uses	Appliances				
	Automotive Applications				
	Medical Devices				
Appearance	Clear/Transparent				
Forms	Film	Film			
Processing Method	Laminating				
	Thermoforming				
Physical	Nominal Value	Unit	Test Method		
Density (23°C)	1.02	g/cm³	ISO 1183		
Water Absorption (Saturation, 23°C)	3.5	%	ISO 62		
Films	Nominal Value	Unit	Test Method		
Tensile Stress			ISO 527-3/100		
MD : Yield	50.0	MPa			
TD : Yield	50.0	MPa			
MD	80.0	MPa			
TD	50.0	MPa			
Tensile Elongation			ISO 527-3/100		

TD : Yield	9.0	%	
MD : Break	> 100	%	
TD : Break	> 100	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	140	°C	
Vicat Softening Temperature	130	°C	ISO 306/B
CLTE - Flow (23 to 80°C)	9.0E-5	cm/cm/°C	ISO 11359-2
Optical	Nominal Value	Unit	Test Method
Gloss			
20°	85		
60°	93		
85°	98		
Refractive Index	1.516		ISO 489
Transmittance <sup>1</sup>	91.8	%	DIN 5036
Haze	2.2	%	ASTM D1003
Yellowness Index	< 1.0	YI	ASTM D1925
Abbe Number	52.0		
NOTE			
1.	Wavelength: 400 - 960 nm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

