

Globalene® 667A

Polypropylene

Lee Chang Yung Chemical Industry Corp.

Message:

Globalene® 667A is a Polypropylene material. It is available in Asia Pacific or North America for blow molding, injection molding, or pipe extrusion. Important attributes of Globalene® 667A are:

Good Stiffness
Impact Resistant
Typical applications include:
Automotive
Bottles
Containers
Plumbing/Piping/Potable Water

General Information	
Features	Good Stiffness
	High Impact Resistance
	Stress Whitening Resistant
Uses	Automotive Applications
	Bottles
	Crates
	Piping
Forms	Pellets
Processing Method	Blow Molding
	Injection Molding
	Pipe Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.901	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.7	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	32.4	MPa	ASTM D638
Tensile Elongation (Yield)	11	%	ASTM D638
Flexural Modulus	1420	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	290	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

