

TEKNIFLEX® COC P15P

PP/COC/PP Film

Tekni-Films, a div of Tekni-Plex

Message:

Thermoformable, FDA-compliant, Pharmaceutical-Grade Cyclic Olefine Copolymer film. Tekni-Plex offers a wide range of polyolefin-based film structures to meet both performance and cost requirements.

General Information		
Uses	Pharmaceuticals	
	Thermoforming Applications	
Agency Ratings	DMF 1378	
	FDA Unspecified Rating	
	USP Unspecified Rating	
Appearance	Clear/Transparent	
Forms	Film	
Processing Method	Thermoforming	
Physical	Nominal Value	Unit
Specific Gravity	1.00	g/cm ³
Dimensional Stability ¹ (140°C)	-3.0 to 3.0	%
Films	Nominal Value	Unit
Film Thickness ²	457	µm
Yield	2.26	m ² /kg
Roll Width ³	< 110.00	cm
Thermoforming Molding Temperature	120 to 160	°C
Tensile Strength - MD (Yield)	21.0	MPa
Oxygen Transmission Rate (23°C, 100% RH)	65	cm ³ /m ² /24 hr
Water Vapor Transmission Rate (38°C, 90% RH)	0.20	g/m ² /24 hr
Optical	Nominal Value	Unit
Haze	15	%
NOTE		
1.	30 minutes	
2.	Thickness tolerance: ±10%	
3.	Roll width tolerance: ±1.5 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

