

ICORENE® 3575

Medium Density Polyethylene

ICO Polymers EMEA, A Division of A. Schulman

Message:

ICORENE® 3575 is a hexene medium density polyethylene with outstanding processability, specifically developed for rotational moulding. This grade is suitable for use in general purpose applications. It has a good balance of properties such as toughness, easy flow and stiffness. ICORENE® 3575 is fully UV stabilized.

General Information			
Additive	UV Stabilizer		
Features	Good Processability		
	Good Stiffness		
	Good Toughness		
	Good UV Resistance		
	High Flow		
Uses	Containers		
	General Purpose		
Appearance	Natural Color		
	Unspecified Color		
Forms	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.935	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	17.0	MPa	ASTM D638
Tensile Elongation (Break)	> 450	%	ASTM D638
Flexural Modulus	650	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Drop Impact Resistance ¹ (-20°C)	170	J/cm	Internal Method
NOTE			

1. Based on ISO 6603

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT