

# EVERLON® TYC-60C

Styrene Butadiene Styrene Block Copolymer

Ever Polymer Co., Ltd.

## Message:

Common grade: base on SBS.

Excellent bonding with PS and HIPS.

General Information			
Features	Bondability		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	6.37	MPa	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Tear Strength	44.1	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

