DynaChar™ 2430-TH

Thermoplastic Polyurethane Elastomer Polymer Dynamix

Message:

Automotive

Flame Retardant TPU
Features:
Excellent Chemical Resistance
Low Temperature Properties
Good Processability
Applications:
Wire & Cable
Industrial

General Information				
Additive	Flame Retardant			
Features	Flame Retardant			
	Good Chemical Resistance			
	Good Processability			
	Low Temperature Impact Resistance			
	Low Temperature Strength			
	Low Temperature Toughness			
Uses	Automotive Applications			
	Industrial Applications			
	Wire & Cable Applications			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	13 to 15	g/10 min	ASTM D1238	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	85		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	31.0	MPa	ASTM D638	
Tensile Elongation (Break)	> 500	%	ASTM D638	
Flexural Modulus	23.8	МРа	ASTM D790	
Flammability	Nominal Value		Test Method	
Flame Rating (1.59 mm)	V-0		UL 94	
Injection	Nominal Value	Unit		
Drying Temperature	76.7 to 87.8	°C		
Drying Time	3.0 to 6.0	hr		
Rear Temperature	182 to 193	°C		

Middle Temperature	191 to 202	°C
Front Temperature	199 to 210	°C
Nozzle Temperature	199 to 210	°C
Processing (Melt) Temp	199 to 210	°C
Mold Temperature	10.0 to 37.8	°C
Injection Pressure	68.9 to 138	MPa
Injection Rate	Moderate	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Clamp Tonnage	5.5 to 8.3	kN/cm²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

