

RheTech Polypropylene G13P100-332UV

Polypropylene

RheTech, Inc.

Message:

13% Glass Fiber Reinforced, UV Stabilized, Polypropylene, (GM 9772) Light Neutral.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 13% filler by weight		
Additive	UV stabilizer		
Features	Good UV resistance		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.988	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	72		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	55.2	MPa	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	43	J/m	ASTM D256
Dart Drop Impact	0.339	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	153	°C	ASTM D648
1.8 MPa, not annealed	132	°C	ASTM D648
Injection	Nominal Value	Unit	Test Method
Drying Temperature	65.6 - 82.2	°C	
Drying Time	1.0 - 2.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	193 - 221	°C	
Middle Temperature	199 - 227	°C	
Front Temperature	204 - 232	°C	
Nozzle Temperature	210 - 221	°C	
Mold Temperature	26.7 - 48.9	°C	
Injection Pressure	2.76 - 10.3	MPa	
Holding Pressure	2.07 - 8.27	MPa	
Back Pressure	0.345 - 1.03	MPa	

Injection instructions

Injection Speed: Variable - Application Dependant
Screw RPM: Recovery 3 seconds before mold opens
Cycle Time: Wall Thickness Dependant

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

