

# Halene P M315

Polypropylene Impact Copolymer

Haldia Petrochemicals Ltd.

Message:

M315 is a Heterophasic Polypropylene Impact Copolymer (PPiCP), produced by the latest generation Spheripol II Technology. This PPiCP is primarily suitable for Injection Molding process. It is recommended for use in injection molding processes where high flow and medium impact strength are required.

General Information			
Features	General Purpose		
	High Flow		
	Impact Copolymer		
	Medium Impact Resistance		
Uses	General Purpose		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density <sup>1</sup>	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Injection Molded)	25.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	6.0	%	ASTM D638
Flexural Modulus (Injection Molded)	1050	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	60	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	87.0	°C	ASTM D648
Vicat Softening Temperature	140	°C	ASTM D1525 <sup>2</sup>
Injection	Nominal Value	Unit	
Rear Temperature	180 to 210	°C	
Middle Temperature	180 to 210	°C	
Front Temperature	180 to 210	°C	
Mold Temperature	30.0 to 40.0	°C	
NOTE			
1.	23°C		
2.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

