

# EMERGE™ PC/ABS 7590

Advanced Resin

Trinseo

## Message:

EMERGE™ PC/ABS 7590 advanced resin is an ignition-resistant PC/ABS blend that contains no chlorine or bromine additives. Its superior processing makes it ideal for molding large parts and optimizing cycle time productivity in injection molding operations. It has a UL 94 flammability rating of V-0 at 1.5mm. This resin is suitable for use in a wide variety of applications in the information technology equipment and consumer electronics (ITE/CE) markets.

Main Characteristics:

UL 94 V-0 at 1.5 mm

Does not contain chlorine or bromine additives

Applications:

TV, monitor and PC enclosures

Adaptors and chargers

General Information			
UL YellowCard	E206114-100716168		
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
Uses	Electrical/Electronic Applications		
	Housings		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/3.8 kg	17	g/10 min	
260°C/5.0 kg	75	g/10 min	
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.20 mm, Injection Molded	62.1	MPa	
Break, 3.20 mm, Injection Molded	46.2	MPa	
Tensile Elongation			ASTM D638
Yield, 3.20 mm, Injection Molded	4.0	%	
Break, 3.20 mm, Injection Molded	50	%	
Flexural Modulus (3.20 mm, Injection Molded)	2830	MPa	ASTM D790
Flexural Strength (3.20 mm, Injection Molded)	97.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	93.9	°C	
1.8 MPa, Unannealed	82.2	°C	
Vicat Softening Temperature	108	°C	ASTM D1525 <sup>1</sup>
Flammability	Nominal Value	Unit	Test Method
Flame Rating <sup>2</sup> (1.50 mm)	V-0		UL 94
Oxygen Index <sup>3</sup>	29	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	79.4 to 90.6	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	220 to 250	°C	
Mold Temperature	60.0 to 90.6	°C	
NOTE			

1. Rate B (120°C/h), Loading 1 (10 N)

2. This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.

3. This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT