

DESLEN™ DSC501G4

Polypropylene

DESCO Co., Ltd.

Message:

Descriptions: DESLEN™ DSC501G4 is Polypropylene Glass Filler 20% reinforced resin. It has good rigidity and Impact resistance.

Applications: DESLEN™ DSC501G4 has good mechanical property and rigidity and it is applied to electronic parts and automotive parts.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Features	Rigidity, high		
	Impact resistance, good		
	Thermal stability, good		
Uses	Electrical/Electronic Applications		
	Application in Automobile Field		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 - 0.60	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	73.5	MPa	ASTM D638
Tensile Elongation (Break)	8.0	%	ASTM D638
Flexural Modulus	3920	MPa	ASTM D790
Flexural Strength	108	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	150	°C	ASTM D648
1.8 MPa, not annealed	135	°C	ASTM D648
Melting Temperature	163	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Suggested Max Moisture	< 0.20	%	

Rear Temperature	190 - 200	°C
Middle Temperature	200 - 210	°C
Front Temperature	200 - 210	°C
Nozzle Temperature	200 - 220	°C
Processing (Melt) Temp	200 - 220	°C
Mold Temperature	40.0 - 60.0	°C

Injection instructions

Speed: 40 to 70%Pressure 1st: 30 to 60%Pressure 2nd: 30 to 60Holding Pressure: 10 to 20%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

