

NYLOY® MG-1113B

Polyamide 66
Nytex Composites Co., Ltd.

Message:
NYLOY® MG-1113B is a Polyamide 66 (Nylon 66) material filled with 13% glass fiber. It is available in Asia Pacific or North America. Primary attribute of NYLOY® MG-1113B: Impact Modified.

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Additive	Impact Modifier		
Features	Impact Modified		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.00	g/cm ³	ASTM D792
--	1.18	g/cm ³	ISO 1183
Molding Shrinkage			
Flow	0.78	%	ASTM D955, ISO 294-4
Across Flow	1.1	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	94		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	71.6	MPa	ASTM D638
--	65.0	MPa	ISO 527-2
Tensile Elongation			
Break	3.0	%	ASTM D638
Break	2.6	%	ISO 527-2
Flexural Modulus			
--	3630	MPa	ASTM D790
--	3400	MPa	ISO 178
Flexural Strength			
--	111	MPa	ASTM D790
--	102	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C, 3.18 mm)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	195	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

