

VESTAMID® D D22

Polyamide 612
Evonik Industries AG

Message:

Characterization: high-viscosity base product
Applications: monofilaments, bristles with high recovery for paint brushes and tooth brushes, abrasive bristles, pipes
Its advantages over PA 12 exhibit in the
heat deflection temperature (melting point nearly 40 °C higher)
tensile and flexural strength
outstanding recovery at high wet strength
The PA 612 compounds of the VESTAMID® D series consequently represent specialty products that complement the comprehensive selection of PA 12 compounds of the VESTAMID® L series.

General Information				
Features	Food Contact Acceptable			
	Fuel Resistant			
	Good Abrasion Resistance			
	Grease Resistant			
	High ESCR (Stress Crack Resist.)			
	High Impact Resistance			
	High Viscosity			
	Oil Resistant			
	Solvent Resistant			
Uses	Monofilaments			
	Piping			
Agency Ratings	EU 10/2011			
	FDA 21 CFR 177.1500			
Appearance	Black			
	Natural Color			
Forms	Granules			
Processing Method	Extrusion			
	Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.06	1.06	g/cm ³	ISO 1183
Molding Shrinkage ¹				ISO 294-4
Across Flow	1.1	--	%	
Flow	1.3	--	%	

Water Absorption				ISO 62
Saturation, 23°C	2.7	--	%	
Equilibrium, 23°C, 50% RH	1.0	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2200	1700	MPa	ISO 527-2/1A
Tensile Stress (Yield)	60.0	49.0	MPa	ISO 527-2/1A
Tensile Strain				ISO 527-2/1A
Yield	4.0	20	%	
Break	> 50	> 50	%	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C, Complete Break	7.0	6.0	kJ/m ²	
23°C, Complete Break	7.0	10	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed ²	170	170	°C	ISO 75-2/B
0.45 MPa, Unannealed	140	140	°C	ISO 75-2/B
1.8 MPa, Unannealed ³	75.0	--	°C	ISO 75-2/A
1.8 MPa, Unannealed	60.0	55.0	°C	ISO 75-2/A
Vicat Softening Temperature	180	180	°C	ISO 306/B
Melting Temperature ⁴	215	215	°C	ISO 11357-3
CLTE - Flow (23 to 55°C)	1.3E-4	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+14	ohms·cm	IEC 60093
Electric Strength	27	27	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
100 Hz	3.80	5.00		
1 MHz	3.00	3.70		
Dissipation Factor				IEC 60250
100 Hz	0.023	0.065		
1 MHz	0.029	0.055		
Comparative Tracking Index ⁵ (Solution A)	> 600	> 600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	HB		

3.20 mm	HB	HB	
Additional Information	Dry	Conditioned	Test Method
Electrolytical Corrosion	A1	A1	IEC 60426
ISO Shortname	PA612, LN, 18-020	--	ISO 1874

NOTE			
1.	specimen 127x12.7x3.2 mm processing acc. to ISO 1874-2		
2.	after conditioning at 180 °C / 60 min		
3.	after conditioning at 180 °C / 60 min		
4.	2nd Heating		
5.	50 drops Value		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT