

# Double Elephant SX-303

Polymethyl Methacrylate Acrylic  
Suzhou Double Elephant Optical Material Co., LTD.

Message:  
Molding compound with excellent heat resistance, mechanical strength and good light transmission, low flow property than SX-302.  
Application: Injection molding compounds, such as automobile instruments and lamps

General Information			
Features	High Heat Resistance		
Uses	Automotive Applications		
	Containers		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	4.0	g/10 min	ISO 1133
Water Absorption (Saturation, 23°C)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	75.0	MPa	ISO 527-2
Tensile Strain (Break)	5.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.5	kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	98.0	°C	ISO 75-2/A
Vicat Softening Temperature	106	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+16	ohms	
Volume Resistivity	> 1.0E+14	ohms · cm	GB/T 1410
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ISO 489
Transmittance	92.0 to 93.0	%	ISO 13468

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

