Haprez™ 3745 LV

Thermoplastic

Hapco Inc.

Message:

A low viscosity, room curing, unfilled polymer system that can be used as a multi-purpose laminating resin for applications requiring wet-out. Its excellent handling characteristics make it easy to mix and use, and HAPREZ 3745 LV gels rapidly, and provides excellent wetting of chopped or woven fiberglass. It is suitable for hand lay-up, or can be sprayed with conventional internal mixing equipment.

HAPREZ 3745 LV can also be filled with high loadings of Fill-it, sand, or aluminum for casting and mock-ups requiring higher temperature application

| General Information | | |
|--------------------------------|----------------------|------|
| Features | High Heat Resistance | |
| | Low Viscosity | |
| | | |
| Uses | Binder | |
| | General Purpose | |
| | Laminates | |
| | | |
| Appearance | Clear Amber | |
| Forms | Liquid | |
| Processing Method | Casting | |
| | Hand Lay-up | |
| | Spraying | |
| | | |
| Hardness | Nominal Value | |
| Durometer Hardness (Shore D) | 82 | |
| Mechanical | Nominal Value | Unit |
| Tensile Strength | 48.3 | MPa |
| Flexural Strength | 68.9 | MPa |
| Compressive Strength | 172 | MPa |
| Thermoset | Nominal Value | Unit |
| Thermoset Mix Viscosity (24°C) | 1000 | сР |
| Gel Time (25°C) | 45.0 | min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

