

Infino ASF-9810FL

Polybutylene Terephthalate

LOTTE ADVANCED MATERIALS CO., LTD.

Message:

Infino ASF-9810FL is a polybutene terephthalate (PBT) product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: automotive industry.

General Information			
Features	General		
Uses	Application in Automobile Field		
Physical	Nominal Value	Unit	Test Method
Specific Gravity (Natural)	1.31	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	40	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow: 3.20mm	1.8 - 2.0	%	ASTM D955
Transverse flow: 3.20mm	1.8 - 2.0	%	ASTM D955
Lateral flow: 3.20mm	1.8 - 2.0	%	ISO 2577
Traffic: 3.20mm	1.8 - 2.0	%	ISO 2577
Water Absorption			
Equilibrium, 23°C	0.40	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.40	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class r	116		ASTM D785
R scale	116		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2300	MPa	ASTM D638
--	2300	MPa	ISO 527-2/50
Tensile Strength			
Yield ²	58.8	MPa	ASTM D638
Yield	58.0	MPa	ISO 527-2/50
Fracture ³	49.0	MPa	ASTM D638
Fracture	49.0	MPa	ISO 527-2/50
Tensile Elongation			
Fracture ⁴	50	%	ASTM D638
Fracture	50	%	ISO 527-2/50
Flexural Modulus			
-- ⁵	2500	MPa	ASTM D790
-- ⁶	2300	MPa	ISO 178

Flexural Strength			
-- ⁷	83.4	MPa	ASTM D790
-- ⁸	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	5.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	34	J/m	ASTM D256
23°C, 6.35 mm	39	J/m	ASTM D256
23°C ¹⁰	4.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 6.40mm	165	°C	ASTM D648
0.45 MPa, unannealed, 4.00mm	160	°C	ISO 75-2/B
1.8 MPa, not annealed, 4.00mm	60.0	°C	ISO 75-2/A
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	50 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	2.8 mm/min		
8.	2.0 mm/min		
9.	Thickness: 4mm		
10.	Thickness: 4mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

