

ELASTOSIL® R 760/70

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV

Extrudates, Automotive, Plastics and Rubber Processing

Hoses, Turbocharge, Automotive & Transportation

Hoses, Automotive, Automotive & Transportation

General Information	
Features	Low Compression Set
Uses	Automotive Applications
	Automotive Under the Hood
	Hose
Processing Method	Calendering
	Extrusion
	Profile Extrusion

Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	70		DIN 53505
Tensile Strength	10.5	MPa	DIN 53504
Tensile Elongation at Break	480	%	DIN 53504
Compression Set	10	%	DIN ISO 815-B
Tear Strength	27.0	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

