

# Axiall PVC 12871

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

Non-lead stabilized CATV jacket

General Information			
Features	Low (to None) Lead Content		
Uses	Wire & Cable Applications		
	Wire Jacketing		
Wire Types	CATV		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44 to 1.48	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	84 to 90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	17.2	MPa	
100% Strain	11.7	MPa	
Tensile Elongation (Break)	290	%	ASTM D638
Aging	Nominal Value	Unit	Test Method
Retention of Tensile Elongation - 10 days (100°C, 762.0 μm)	78	%	UL 1581
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-24.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	29	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Melt Temperature	177	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT