ELASTOSIL® R 861/70

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV

Uncured Properties

Hoses, Automotive, Automotive & Transportation

Membranes, Plastics and Rubber Processing

Membranes, Automotive & Transportation

Molded Seals, Plastics and Rubber Processing

Photocopier Rolls, Printing Industry

Extrudates, Technical, Plastics and Rubber Processing

Extrudates, food contact, Plastics and Rubber Processing

Extrudates, Automotive, Plastics and Rubber Processing

Extrudates, Automotive, Automotive & Transportation

Cable, general purpose, Plastics and Rubber Processing

Cable, general purpose, Construction

Cable, general purpose, Energy & Electrical Engineering

Cable, general purpose, Automotive & Transportation

Molded Parts, Technical, Plastics and Rubber Processing

Molded Parts, Food Contact, Plastics and Rubber Processing Molded Parts, Automotive, Plastics and Rubber Processing

General Information		
Features	Food Contact Acceptable	
	High Elasticity	
	Low Compression Set	
Uses	Automotive Applications	
	Compounding	
	Gaskets	
	Hose	
	Membranes	
	Profiles	
	Seals	
	Valves/Valve Parts	
	Wire & Cable Applications	
Processing Method	Calendering	
	Compression Molding	
	Extrusion	
	Press Molding	
	Profile Extrusion	
	Wire & Cable Extrusion	

Unit

Test Method

Nominal Value

Color	Translucent			
Density	1.20	g/cm³	ISO 1183	
Cured Properties	Nominal Value	Unit	Test Method	
Shore Hardness (Shore A)	70		DIN 53505	
Tensile Strength	8.90	MPa	DIN 53504	
Tensile Elongation at Break	310	%	DIN 53504	
Compression Set	20	%	DIN ISO 815-B	
Tear Strength	18.0	kN/m	ASTM D624B	
Rebound Resilience	51	%	DIN 53512	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

