

Firestone C200-001

Polyamide 6
Firestone Textiles Company

Message:

Firestone C200-001 is a polyamide 6 (nylon 6) material. This product is available in North America and is processed by compounding, extrusion or injection molding. The main characteristics of Firestone C200-001 are: lubrication.

The typical application fields of Firestone C200-001 are: additives/masterbatches

General Information	
Additive	Lubricant
Features	Lubrication
Uses	Composite
Appearance	Natural color
Forms	Particle
Processing Method	Composite
	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	82.7	MPa	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	180	°C	ASTM D648
1.8 MPa, not annealed	65.0	°C	ASTM D648
Melting Temperature	220	°C	

Additional Information		
Relative Viscosity, Test Method Unspecified:Sulfuric Acid: 3.10Formic Acid: 82Chip Size: 2 x 3.5 mm		
Extrusion	Nominal Value	Unit
Suggested Max Moisture	0.080	%
Cylinder Zone 1 Temp.	249 - 260	°C
Cylinder Zone 3 Temp.	254 - 266	°C
Cylinder Zone 4 Temp.	254 - 266	°C
Cylinder Zone 5 Temp.	260 - 271	°C
Melt Temperature	260 - 271	°C

Extrusion instructions

Max Melt Temp: 515 - 550°F Quench: 65 - 75°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

