

Generic PUR-Est/eth,TDI

Polyurethane (Polyester/Polyether mix, TDI)

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic PUR-Est/eth,TDI
This information is provided for comparative purposes only.

General Information			
Hardness	Nominal Value		Test Method
Durometer Hardness (23°C)	70 to 90		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain, 23°C)	1.54 to 33.1	MPa	ASTM D412
Compression Set	23 to 42	%	ASTM D395
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity	370 to 6400	cP	ASTM D2393
Demold Time	15 to 180	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT