Shin-Etsu Elastomer KE-961TU

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

KE-961TU is one of a series of easy processing, general purpose silicone rubber bases. It can be used in a variety of applications requiring finishing by molding (compression,injection,transfer). Rubber contacts. Food packing. Industrial packing. Diaphragms.

| General Information | | |
|--------------------------------|------------------------|-------------------|
| Features | Workability, good | |
| | General | |
| | | |
| Uses | Diaphragm | |
| | Industrial application | |
| | Food packaging | |
| | General | |
| | | |
| Processing Method | Resin transfer molding | |
| | Compression molding | |
| | Injection molding | |
| | | |
| Physical | Nominal Value | Unit |
| Specific Gravity | 1.18 | g/cm ³ |
| Hardness | Nominal Value | Unit |
| Durometer Hardness | 60 | |
| Elastomers | Nominal Value | Unit |
| Tensile Strength | 9.17 | MPa |
| Tensile Elongation (Break) | 320 | % |
| Tear Strength ¹ | 9.81 | kN/m |
| Compression Set (149°C, 22 hr) | 10 | % |
| Thermoset | Nominal Value | Unit |
| Post Cure Time (200°C) | 4.0 | hr |
| Additional Information | Nominal Value | Unit |
| Cure Agent | DBPH | |
| Press / Post Cure: Post | | |
| NOTE | | |
| 1. | B mould | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

