

WEVO-CHEMIE Polyurethanes PD 52/385

Polyurethane
WEVO-CHEMIE GmbH

Message:

WEVO-CHEMIE Polyurethanes PD 52/385 is a Polyurethane material. It is available in Europe or North America for casting.

Important attributes of WEVO-CHEMIE Polyurethanes PD 52/385 are:

- Flame Rated
- Good Adhesion
- Good Flexibility
- Typical applications include:
 - Adhesives/Tapes
 - Automotive

General Information			
Features	Good Adhesion		
	Good Flexibility		
Uses	Adhesives		
	Automotive Applications		
	Automotive Electronics		
	Bonding		
Forms	Liquid		
Processing Method	Casting		
Physical	Nominal Value	Unit	
Water Absorption ¹ (Saturation, 23°C)	0.50	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-60.0	°C	TMA
Thermal Conductivity	0.30	W/m/K	ISO 22007-2
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Hardener	Mix Ratio by Weight: 26		
Resin	Mix Ratio by Weight: 100		
Pot Life (22°C)	5.0 to 30	min	
Thermoset Mix Viscosity ² (22°C)	1200 to 2000	cP	
Additional Information	Nominal Value	Unit	Test Method
Operating Temperature	-60 to 125	°C	
Uncured Properties	Nominal Value	Unit	Test Method
Density			
22°C ³	1.06 to 1.09	g/cm³	

22°C ⁴	1.20 to 1.24	g/cm ³	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	75 to 80		ISO 868
Tensile Strength	9.00	MPa	ISO 527
Tensile Elongation at Break	210	%	ISO 527
Electric Strength	23	kV/mm	IEC 60243
Relative Permittivity (50 Hz, 23°C)	3.00		IEC 60250
Volume Resistivity	4.0E+14	ohms·cm	IEC 60093
NOTE			
1.	30 Days		
2.	Rotational viscometer		
3.	Resin		
4.	Hardener		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT