

POLYFORT® FPP 40 T

Polypropylene Homopolymer

A. Schulman Europe

Message:

40% talc filled PP-Homopolymer

General Information			
UL YellowCard	E86615-252216		
Filler / Reinforcement	Talc filler, 40% filler by weight		
Features	Homopolymer		
UL File Number	E86615		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	6.00	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	85.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4000	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	28.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	2.5	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	1.5	kJ/m ²	ISO 179/1eA
23°C	2.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	10	kJ/m ²	ISO 179/1eU
23°C	18	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	118	°C	ISO 75-2/Bf
1.8 MPa, not annealed	69.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	151	°C	ISO 306/A50
--	92.0	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Flammability	Nominal Value	Unit	Test Method
Burning Rate (2.00 mm)	< 100	mm/min	ISO 3795
Flammability Classification			IEC 60695-11-10, -20

1.50 mm	HB		IEC 60695-11-10, -20
3.00 mm	HB		IEC 60695-11-10, -20
Glow Wire Flammability Index			IEC 60695-2-12
1.50 mm	775	°C	IEC 60695-2-12
3.00 mm	775	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.50 mm	800	°C	IEC 60695-2-13
3.00 mm	800	°C	IEC 60695-2-13

Additional Information

- 1.)
 Not for use in food contact applications2.)
 Not for use in medical or pharmaceutical applications

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

