

DINALON® B2S25 V2-7035

Polyamide 6

Grupo Repol

Message:

DINALON® B2S25 V2-7035 is a Polyamide 6 (Nylon 6) product. It is available in Europe.

Characteristics include:

- Flame Rated
- Flame Retardant
- Halogen Free
- High Viscosity

General Information			
Features	Flame Retardant		
	Halogen Free		
	High Viscosity		
Appearance	Grey		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183/A
Humidity ¹	< 0.25	%	ISO 15512/A
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3300	MPa	ISO 527-2
Tensile Stress (Break)	75.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Flexural Modulus	1800	MPa	ISO 178
Flexural Stress	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	55.0	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	°C	ISO 306/B
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-2		UL 94
NOTE			

1. Karl-Fischer

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

