# HiFill® PP GF20 CC LE

## Polypropylene

## **Techmer Engineered Solutions**

#### Message:

HiFill® PP GF20 CC LE is a Polypropylene product filled with 20% glass fiber. It can be processed by injection molding and is available in North America. Typical application: Food Contact Applications.

Characteristics include:

Flame Rated

Chemically Coupled

General Information					
Filler / Reinforcement	Glass Fiber,20% Filler by Weight				
Features	Chemically Coupled				
	Low Extractables				
Agency Ratings	FDA Unspecified Rating				
Appearance	Colors Available				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.04	g/cm³	ASTM D792		
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955		
Water Absorption (24 hr)	0.010	%	ASTM D570		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	112		ASTM D785		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	68.9	МРа	ASTM D638		
Tensile Elongation (Break)	4.0	%	ASTM D638		
Flexural Modulus	4310	MPa	ASTM D790		
Flexural Strength	114	МРа	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256		
Unnotched Izod Impact (3.18 mm)	590	J/m	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load			ASTM D648		
0.45 MPa, Unannealed	163	°C			
1.8 MPa, Unannealed	154	°C			
Melting Temperature	163	°C			
CLTE - Flow	3.4E-5	cm/cm/°C	ASTM D696		
Electrical	Nominal Value	Unit	Test Method		
Volume Resistivity	4.0E+16	ohms·cm	ASTM D257		

Dielectric Strength <sup>1</sup>	21	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	НВ		UL 94
NOTE			

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

