

# Unichem 7811C3-02

Polyvinyl Chloride

Colorite Polymers

## Message:

Unichem 7811C3-02 is a Polyvinyl Chloride product. It is available in North America. Applications of Unichem 7811C3-02 include food contact applications and medical/healthcare.

Characteristics include:

Good Flexibility

Non-Toxic

| General Information          |                                 |                   |             |
|------------------------------|---------------------------------|-------------------|-------------|
| Features                     | Good Flexibility                |                   |             |
|                              | Non-Toxic                       |                   |             |
| Uses                         | Food Service Applications       |                   |             |
|                              | Medical/Healthcare Applications |                   |             |
| Appearance                   | Clear/Transparent               |                   |             |
| Forms                        | Pellets                         |                   |             |
| Physical                     | Nominal Value                   | Unit              | Test Method |
| Specific Gravity             | 1.22                            | g/cm <sup>3</sup> | ASTM D792   |
| Hardness                     | Nominal Value                   | Unit              | Test Method |
| Durometer Hardness (Shore A) | 78                              |                   | ASTM D2240  |
| Mechanical                   | Nominal Value                   | Unit              | Test Method |
| Tensile Strength (Yield)     | 17.2                            | MPa               | ASTM D638   |
| Tensile Elongation (Yield)   | 350                             | %                 | ASTM D638   |
| Elastomers                   | Nominal Value                   | Unit              | Test Method |
| Tensile Stress (100% Strain) | 8.27                            | MPa               | ASTM D412   |
| Thermal                      | Nominal Value                   | Unit              | Test Method |
| Brittleness Temperature      | -31.1                           | °C                | ASTM D746   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT