

Estane® 2103-90AENH TPU

Thermoplastic Polyurethane Elastomer (Polyether)

Lubrizol Advanced Materials, Inc.

Message:

2103-90AENH is a thermoplastic polyurethane elastomer.

Feature: NSF Standard 61 Certified, FDA Compliance

General Information			
Agency Ratings	FDA not rated		
	NSF 61		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (224°C/8.7 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.60	%	ASTM D955
Transverse flow	0.70 - 1.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	90		ASTM D2240
Shaw D	47		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 g, H-22 Wheel)	50.0	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% strain, 3.20mm	6.20	MPa	ASTM D412
100% strain, 3.20mm	9.00	MPa	ASTM D412
300% strain, 3.20mm	17.2	MPa	ASTM D412
Tensile Strength (Break, 3.20 mm)	48.2	MPa	ASTM D412
Tensile Elongation (Break, 3.20 mm)	560	%	ASTM D412
Tensile Elongation at Break (3.20 mm)	60	%	ASTM D412
Tear Strength ¹ (3.20 mm)	126	kN/m	ASTM D624
Compression Set			ASTM D395B
25°C, 22 hr	25	%	ASTM D395B
70°C, 22 hr	40	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-34.0	°C	DSC
Vicat Softening Temperature	90.0	°C	ASTM D1525 ²

CLTE - Flow	1.6E-4	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	
Drying Temperature	88.0 - 104	°C	
Processing (Melt) Temp	193 - 210	°C	
Mold Temperature	16.0 - 60.0	°C	
Injection instructions			
Air Dew Point: <-40°C			
Extrusion	Nominal Value	Unit	
Drying Temperature	88.0 - 104	°C	
Melt Temperature	188 - 204	°C	
Extrusion instructions			
Air Dew Point: <-40°C			
NOTE			
1.	C mould		
2.	标准 B (120°C/h), 压力1 (10N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT