

HiFill® PP 0096 S LE

Polypropylene

Techmer Engineered Solutions

Message:

HiFill® PP 0096 S LE is a Polypropylene product filled with filler. It can be processed by injection molding and is available in North America. Typical application: Food Contact Applications.

General Information			
Filler / Reinforcement	Filler		
Features	Low Extractables		
Agency Ratings	FDA Unspecified Rating		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.9	%	ASTM D955
Water Absorption (24 hr)	0.050	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	33.1	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	1310	MPa	ASTM D790
Flexural Strength	35.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	116	°C	
1.8 MPa, Unannealed	54.4	°C	
CLTE - Flow	3.4E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

