

ESTOPLAST XU 520BB01

Polyamide 6
Ester Industries Ltd.

Message:

Polyamide 6 - Unfilled, Impact Modified (Toughened)
Automotive: Intake manifold, Electrical components and connectors
Electrical & Electronic: Lighting, Power connectors ,

General Information			
Additive	Impact modifier demoulding		
Features	Impact modification Impact resistance, high Good demoulding performance		
Uses	Lighting Applications Electrical/Electronic Applications Connector Application in Automobile Field		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm ³	ASTM D792
Molding Shrinkage	1.4	%	ISO 294-4
Water Absorption			ISO 62
Saturated, 23°C	5.8	%	ISO 62
Equilibrium, 23°C, 50% RH	2.1	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	49.0	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Strength	72.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	140	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	205	°C	ASTM D648
Peak Melting Temperature	222	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method

Dielectric Strength	25	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	85 - 90	°C	
Drying Time	3.0 - 4.0	hr	
Rear Temperature	230 - 250	°C	
Middle Temperature	235 - 250	°C	
Nozzle Temperature	235 - 255	°C	
Processing (Melt) Temp	240 - 265	°C	
Mold Temperature	55 - 80	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

