

Silastic® Q7-4750

Silicone
Dow Corning Corporation

Message:

Raw materials for medical device fabrication in the Healthcare Industry

APPLICATIONS

Silastic® BioMedical Grade ETR Elastomers (Q7-4720, Q7-4735, Q7-4750, Q7-4765, and Q7-4780) are heat-cured high consistency silicone rubbers designed for use by customers fabricating medical devices, including those intended for implantation in humans for less than 30 days.

DESCRIPTION

Silastic BioMedical Grade ETR Elastomers (Q7-4720, Q7-4735, Q7-4750, Q7-4765, and Q7-4780) are a series of two-part, enhanced-tear-resistant (ETR) silicone elastomers that consist of dimethyl and methylvinyl siloxane copolymers and reinforcing silica. The elastomers exhibit a range of hardness from soft (20 Shore A) to firm (80 Shore A). Each elastomer is supplied as a two-component kit (Part A and Part B), equal portions (by weight) of which must be thoroughly blended together prior to use. The elastomer is then thermally cured via addition-cure (platinum-cure) chemistry

General Information			
Features	High Gas Permeability		
	No frost		
	Radiation disinfection		
	Pressure cooker disinfection		
	Ethylene oxide disinfection		
	Good coloring		
	High pressure heating resistance		
	Compliance of Food Exposure		
Uses	Medical/nursing supplies		
Agency Ratings	FDA 21 CFR 177.2600		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.7	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	50		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (200% Strain)	2.14	MPa	ASTM D412
Tensile Strength	10.2	MPa	ASTM D412
Tensile Elongation (Break)	900	%	ASTM D412
Tear Strength ¹	45.9	kN/m	ASTM D624
Compression Set	56	%	ASTM D395
NOTE			
1.	B mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

