Lionpol HF-204094

Thermoplastic Elastomer

Lion Polymers Incorporated

Message:

Lionpol HF-204094 is a Thermoplastic Elastomer (TPE) product. It is available in North America. Primary characteristic: high flow.

| General Information | | | |
|---------------------------------------|---------------|----------|-------------|
| Features | High Flow | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 42 | g/10 min | ASTM D1238 |
| Molding Shrinkage | | | ASTM D955 |
| Flow | 1.1 to 1.2 | % | |
| Across Flow | 1.3 to 1.4 | % | |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 94 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress (100% Strain) | 15.5 | MPa | ASTM D412 |
| Tensile Strength (Break) | 16.4 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 190 | % | ASTM D412 |
| Injection | Nominal Value | Unit | |
| Rear Temperature | 182 to 193 | °C | |
| Front Temperature | 199 to 210 | °C | |
| Nozzle Temperature | 216 to 221 | °C | |
| Mold Temperature | 37.8 to 60.0 | °C | |
| Back Pressure | 0.552 to 1.03 | MPa | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

