

ROPOTEN® FV-2-109

Low Density Polyethylene

LUKOIL Bulgaria Ltd.

Message:

Solid product in the form of granules with length ranging from 2 to 6 mm, natural colour, odourless. The product is stable in normal storage and handling conditions.

General Information			
Features	The smell is low to none		
Uses	Films		
	Agricultural application		
Appearance	Natural color		
Forms	Particles		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	> 0.917	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.7 - 2.3	g/10 min	ASTM D1238, ISO 1133
Volatile Matter		%	Internal method
Impurities - 200 g sample			Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 12.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	> 500	%	ASTM D638, ISO 527-2
Optical	Nominal Value	Unit	Test Method
Haze	< 12	%	ASTM D1003
Additional Information	Nominal Value		Test Method

Off-spec granules: 1.7% Max

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT