

# Moplen HP562T

Polypropylene Homopolymer

LyondellBasell Industries

## Message:

Polypropylene Homopolymer Resin for Spunbond Fiber

Features:

Very high melt flow with narrow MWD resin for high speed spin continuity of low denier fiber

Very uniform melt flow rate and low gel

Excellent processability

Good gas fading resistance

Applications:

Spunbonded nonwoven fabric using for hygiene products, medical, agriculture, geotextile, etc.

General Information			
Features	Low speed solidification crystal point		
	Homopolymer		
	Resistance to gas fading		
	Workability, good		
	High liquidity		
	Narrow molecular weight distribution		
Uses	Spunbond nonwoven fabric		
	Fiber		
Processing Method	Fiber (spinning) extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm <sup>3</sup>	ASTM D792B
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	60	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	34.0	MPa	ASTM D638
Tensile Elongation (Yield)	10	%	ASTM D638
Flexural Modulus	1390	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	14	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	107	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

