

PRIMAENE WPP692MB

Metallocene Linear Low Density Polyethylene

Southern Polymer, Inc.

Message:

A metallocene linear low density polyethylene

Applications: - Agricultural film

Barrier food packaging

Blown film

Food packaging

Form and fill and seal packaging

Freezer film

General packaging

Heavy duty bags

Industrial packaging

Lamination film

Multilayer packaging film

Overwrap film

Packaging films

Premium trash bags

Liners

Features:

Outstanding tensile, impact strength and puncture

Excellent drawdown

Slip: zero

Antiblock: 4500 ppm

Processing aid

General Information	
Additive	Antiblock (4500 ppm)
	Processing Aid
Features	Antiblocking
	Good Drawdown
	Good Processability
	High Impact Resistance
	High Tensile Strength
	Low Density
Uses	Agricultural Applications
	Bags
	Blown Film
	Consumer Applications
	Food Packaging
	Heavy-duty Bags
	Industrial Applications
	Laminates
	Liners

Multilayer Film
Non-specific Food Applications
Packaging

Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Secant Modulus			ASTM D882
1% Secant, MD	175	MPa	
1% Secant, TD	182	MPa	
Tensile Strength			ASTM D882
MD : Yield	9.03	MPa	
TD : Yield	8.48	MPa	
MD : Break	46.1	MPa	
TD : Break	32.1	MPa	
Tensile Elongation			ASTM D882
MD : Break	470	%	
TD : Break	550	%	
Dart Drop Impact	580	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	270	g	
TD	440	g	
Thermal	Nominal Value	Unit	
Peak Melting Temperature	119	°C	
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	42		ASTM D2457
Haze	16	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT