

# AFFINITY™ PF 7266

Polyolefin Elastomer  
The Dow Chemical Company

Message:

AFFINITY\* PF 7266 Polyolefin Elastomer is an ethylene based elastomer, offers excellent processing and performance in extrusion applications targeting for CPP film modification application.

Main Characteristics:

Pellet form

Excellent processability

Applications:

Extrusion applications

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.885	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.5	g/10 min	ASTM D1238
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-42.0	°C	Internal method
Vicat Softening Temperature	48.0	°C	ASTM D1525
Melting Temperature (DSC) <sup>1</sup>	76.0	°C	Internal method
Peak Crystallization Temperature	60	°C	Internal method
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

  
WECHAT